



Karnataka Material Test House Pvt. Ltd.,

Soil Investigation, Concrete and NDT Testing, Topo Survey, & Project management Consultancy

CIN No: U74210KA2004PTC035137 G S T No: 29AACCK4994Q1ZI PAN No: AACCK4994Q

Report No	KMTH/Cubes/3615/2022-23					Date	27.06.2022	
TEST RESULTS ON CONCRETE CUBES								
Name of Client & Address	Bruhat Bengaluru Mahanagara Palike Yelahanka Project Division Bengaluru.							
Name of Project & Address	Improvements to Someshwara Hill and Surrounding areas at attur, Ward No-03 in Yelahanka Satellite Town Sub Division.							
Name of Consultant	M/s DSR Infratech, 1594, 3rd main, Judicial Layout, Yelahanka, Bengaluru.							
Name of Agency	Mr. Gopi Reddy Bengaluru.							
Clients Letter Dated	25.06.2022							
Date of Sample Received	25.06.2022							
Source of Sample	Supplied by the Client							
Dimensions of Specimens in mm	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
Grade of Concrete	M20							
Compressive Strength test as per guidelines of IS-516-1959 has been conducted on the concrete cube specimens supplied by the client and the results are tabulated here below								
Sl No	Cubes Pertaining to the concrete Cast at* (Details of structural Member Identification)	Date of Casting*	Date of Testing	Age of Concrete on the date of test** (Days)	Contact Area (mm ²)	Weight of Specimen (gm)	Load In KN	Compressive Strength in Nmm ²
1	Raft Footing Concrete (Drainage Work)	18.06.2022	25.06.2022	7 Days	22500.00	8216	419.6	18.65
2		18.06.2022	25.06.2022		22500.00	8220	426.9	18.97
3		18.06.2022	25.06.2022		22500.00	8214	422.8	18.79

1N/Sq.mm=10kg/Sq.cm(Approx)

* As furnished by the client

Note: A Minimum of three cube specimens shall be supplied for testing as per IS:516-1959

For Karnataka Material Test House Pvt Ltd.,

Prepared & Checked by
Nagaraj K S

Approved by
Narayanswamy B



.....End of Report.....

Asst. Executive Engineer

Note:

- 1) This report is not to be reproduced except in full without our prior permission in writing.
- 2) The results listed refer only to the tested samples and applicable parameters.
- 3) Any correction in the report will be invalid.

Project Division
Yelahanka Zone
BBMP, Bangalore - 92



Off & Lab :No. 8 (10/3), 4th cross, Basaveshwara layout, Nagashettihalli, RMV 2nd Stage, BENGALURU 560094
Tel: 080- 2341 8668, 23511213 Mobile: 94485 15258 E-mail: kmthblr@gmail.com www.karnatakamaterialtesthouse.com
M/s Karnataka Consultancy Services is Sister Concern of KMT HPL



Karnataka Material Test House Pvt. Ltd.,

Soil Investigation, Concrete and NDT Testing, Topo Survey, & Project management Consultancy

CIN No: U74210KA2004PTC035137 G S T No: 29AACCK4994Q1ZI PAN No: AACCK4994Q

Report No	KMTH/Cubes/3616/2022-23					Date	18.07.2022	
TEST RESULTS ON CONCRETE CUBES								
Name of Client & Address	Bruhat Bengaluru Mahanagara Palike Yelahanka Project Division Bengaluru.							
Name of Project & Address	Improvements to Someshwara Hill and Surrounding areas at attur, Ward No-03 in Yelahanka Satellite Town Sub Division.							
Name of Consultant	M/s DSR Infratech, 1594, 3rd main, Judicial Layout, Yelahanka, Bengaluru. Bengaluru.							
Name of Agency	Mr.Gopi Reddy							
Clients Letter Dated	16.07.2022							
Date of Sample Received	16.07.2022							
Source of Sample	Supplied by the Client							
Dimensions of Specimens in mm	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
Grade of Concrete	M20							
Compressive Strength test as per guidelines of IS-516-1959 has been conducted on the concrete cube specimens supplied by the client and the results are tabulated here below								
Sl No	Cubes Pertaining to the concrete Cast at*(Details of structural Member Identification	Date of Casting*	Date of Testing	Age of Concrete on the date of test** (Days)	Contact Area (mm ²)	Weight of Specimen (gm)	Load In KN	Compressive Strength in Nmm ²
1	Raft Footing	18.06.2022	16.07.2022	28 Days	22500.00	8108	630.4	28.02
2	Concrete	18.06.2022	16.07.2022		22500.00	8094	624.5	27.76
3	(Drainage Work)	18.06.2022	16.07.2022		22500.00	8144	620.8	27.59

1N/Sq.mm=10kg/Sq.cm(Approx)

* As furnished by the client

Note: A Minimum of three cube specimens shall be supplied for testing as per IS:516-1959

For Karnataka Material Test House Pvt Ltd.,

Prepared & Checked by
Nagaraj K S

Approved by
Narayanswamy.B

.....End of Report.....

Note:

- 1)This reports is not to be reproduced except in full without prior permission in writing.
- 2)The results listed refer only to the tested samples nd applicable parameters.
- 3)Any correction in the report will be invalid.

Project Executive Engineer
Yelahanka Zone
BBMP, Bangalore - 92



Off & Lab :No. 8 (10/3), 4th cross, Basaveshwara layout, Nagashettihalli, RMV 2nd Stage, BENGALURU 560094
1.:080- 2341 8668, 23511213 Mobile: 94485 15258 E-mail: kmthblr@gmail.com www.karnatakamaterialtesthouse.com
M/S Karnataka Consultancy Services is Sister Concern of KMTHPL



Karnataka Material Test House Pvt. Ltd.,

Soil Investigation, Concrete and NDT Testing, Topo Survey, & Project management Consultancy

CIN No: U74210KA2004PTC035137 G S T No: 29AACCK4994Q1ZI PAN No: AACCK4994Q

Report No	KMTH/Cubes/3617/2022-23					Date	28.06.2022	
TEST RESULTS ON CONCRETE CUBES								
Name of Client & Address	Bruhat Bengaluru Mahanagara Palike Yelahanka Project Division Bengaluru.							
Name of Project & Address	Improvements to Someshwara Hill and Surrounding areas at attur, Ward No-03 in Yelahanka Satelite Town Sub Division.							
Name of Consultant	M/s DSR Infratech, 1594, 3rd main, Judicial Layout, Yelahanka, Bengaluru.							
Name of Agency	Mr.Gopi Reddy Bengaluru.							
Clients Letter Dated	27.06.2022							
Date of Sample Received	27.06.2022							
Source of Sample	Supplied by the Client							
Dimensions of Specimens in mm	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
Grade of Concrete	M20							
Compressive Strength test as per guidelines of IS-516-1959 has been conducted on the concrete cube specimens supplied by								
Sl No	Cubes Pertaining to the concrete Cast at*(Details of structural Member Identification	Date of Casting*	Date of Testing	Age of Concrete on the date of test** (Days)	Contact Area (mm ²)	Weight of Specimen (gm)	Load In KN	Compressive Strength in Nmm ²
1	Wall Concrete	20.06.2022	27.06.2022	7 Days	22500.00	8316	423.4	18.82
2		20.06.2022	27.06.2022		22500.00	8262	426.8	18.97
3		20.06.2022	27.06.2022		22500.00	8246	426.8	18.97

1N/Sq.mm=10kg/Sq.cm(Approx)

* As furnished by the client

Note; A Minimum of three cube specimens shall be supplied fo testing as per IS:516-1959

For Karnataka Material Test House Pvt Ltd.,

Prepared & Checked by
Nagaraj K S

Approved by
Narayanswamy



.....End of Report.....

- Note:
- 1)This reports is not to be reproduced except in full without our prior permission in writing.
 - 2)The results listed refer only to the tested samples nd applicable parameters.
 - 3)Any correction in the report will be invalid.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore



Off & Lab :No. 8 (10/3), 4th cross, Basaveshwara layout, Nagashettihalli, RMV 2nd Stage, BENGALURU 560094
Tel:080- 2341 8668, 23511213 Mobile: 94485 15258 E-mail: kmthblr@gmail.com www.karnatakamaterialtesthouse.com
M/s Karnataka Consultancy Services is Sister Concern of KMTHPL

Karnataka Material Test House Pvt. Ltd.,



CIN No: U74210KA2004PTC035137 G S T No: 29AACCK4994Q1ZI PAN No: AACCK4994Q

Report No	KMTH/Cubes/3618/2022-23					Date	19.07.2022		
TEST RESULTS ON CONCRETE CUBES									
Name of Client & Address	Bruhat Bengaluru Mahanagara Palike Yelahanka Project Division Bengaluru.								
Name of Project & Address	Improvements to Someshwara Hill and Surrounding areas at attur, Ward No-03 in Yelahanka Satelite Town Sub Division.								
Name of Consultant	M/s DSR Infratech, 1594, 3rd main, Judicial Layout, Yelahanka, Bengaluru.								
Name of Agency	Mr.Gopi Reddy							Bengaluru.	
Clients Letter Dated	18.07.2022								
Date of Sample Received	18.07.2022								
Source of Sample	Supplied by the Client								
Dimensions of Specimens in mm	150.0	x	150.0	x	150.0				
	150.0	x	150.0	x	150.0				
	150.0	x	150.0	x	150.0				
Grade of Concrete	M20								
Compressive Strength test as per guidelines of IS-516-1959 has been conducted on the concrete cube specimens									
Sl No	Cubes Pertaining to the concrete Cast at*(Details of structural Member Identification)	Date of Casting*	Date of Testing	Age of Concrete on the date of test** (Days)	Contact Area (mm ²)	Weight of Specimen (gm)	Load In KN	Compressive Strength in Nmm ²	
1	Wall Concrete	20.06.2022	18.07.2022	28 Days	22500.00	8168	630.6	28.03	
2		20.06.2022	18.07.2022		22500.00	8208	628.4	27.93	
3		20.06.2022	18.07.2022		22500.00	8188	627.4	27.88	

1N/Sq.mm=10kg/Sq.cm(Approx)

* As furnished by the client

Note; A Minimum of three cube specimens shall be supplied for testing as per IS:516-1959

For Karnataka Material Test House Pvt Ltd.,

Prepared & Checked by
Nagaraj K S

Approved by
Narayanswamy.B

.....End of Report.....

Asst. Executive Engineer

Project Division

Yelahanka Zone

BBMP, Bangalore

Note:

- 1)This reports is not to be reproduced except in full without our prior permission in writing.
- 2)The results listed refer only to the tested samples nd applicable parameters.
- 3)Any correction in the report will be invalid.



Off & Lab :No. 8 (10/3), 4th cross, Basaveshwara layout, Nagashettihalli, RMV 2nd Stage, BENGALURU 560094
:080- 2341 8668, 23511213 Mobile: 94485 15258 E-mail: kmthblr@gmail.com www.karnatakamaterialtesthouse.com
M/S Karnataka Consultancy Services is Sister Concern of KMT HPL

Karnataka Material Test House Pvt. Ltd.,

Soil Investigation, Concrete and NDT Testing, Topo Survey, & Project management Consultancy

CIN No. U74210KA2004PTC035137 G S T No. 29AACCK4994Q1ZI PAN No. AACCK4994Q



Report No	KMTH/Cubes/3619/2022-23						Date	06.06.2022
TEST RESULTS ON CONCRETE CUBES								
Name of Client & Address	Bruhat Bengaluru Mahanagara Palike Yelahanka Project Division Bengaluru.							
Name of Project & Address	Improvements to Someshwara Hill and Surrounding areas at attur, Ward No-03 in Yelahanka Satellite Town Sub Division.							
Name of Consultant	M/s DSR Infratech, 1594, 3rd main, Judicial Layout, Yelahanka, Bengaluru.							
Name of Agency	Mr.Gopi Reddy Bengaluru.							
Clients Letter Dated	04.06.2022							
Date of Sample Received	04.06.2022							
Source of Sample	Supplied by the Client							
Dimensions of Specimens in mm	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
Grade of Concrete	M20							
Compressive Strength test as per guidelines of IS-516-1959 has been conducted on the concrete cube specimens supplied by								
Sl No	Cubes Pertaining to the concrete Cast at*(Details of structural Member Identification	Date of Casting*	Date of Testing	Age of Concrete on the date of test** (Days)	Contact Area (mm ²)	Weight of Specimen (gm)	Load In KN	Compressive Strength in Nmm ²
1	Plinth Beam Concrete (Compound Work)	28.05.2022	04.06.2022	7 Days	22500.00	8268	416.8	18.52
2		28.05.2022	04.06.2022		22500.00	8254	420.7	18.70
3		28.05.2022	04.06.2022		22500.00	8266	415.2	18.45

1N/Sq.mm=10kg/Sq.cm(Approx)
Note; A Minimum of three cube specimens shall be supplied for testing as per IS:516-1959

For Karnataka Material Test House Pvt Ltd.,

Prepared & Checked by
Nagaraj K S

Approved by
Narayanswamy.B

.....End of Report.....

Asst. Executive Engineer
Project Division

Yelahanka Zone
BBMP, Bangalore

- Note:
- 1)This reports is not to be reproduced except in full without our prior permission in writing.
 - 2)The results listed refer only to the tested samples and applicable parameters.
 - 3)Any correction in the report will be invalid.



Off & Lab :No. 8 (10/3), 4th cross, Basaveshwara layout, Nagashettihalli, RMV 2nd Stage, BENGALURU 560094
:080- 2341 8668, 23511213 Mobile: 94485 15258 E-mail: kmthblr@gmail.com www.karnatakamaterialtesthouse.com
M/s Karnataka Consultancy Services is Sister Concern of KMT HPL



Karnataka Material Test House Pvt. Ltd.,

Soil Investigation, Concrete and NDT Testing, Topo Survey, & Project management Consultancy

CIN No: U74210KA2004PTC035137 G S T No: 29AACCK4994Q1ZI PAN No: AACCK4994Q

Report No	KMTH/Cubes/3620/2022-23					Date	27.06.2022	
TEST RESULTS ON CONCRETE CUBES								
Name of Client & Address	Bruhat Bengaluru Mahanagara Palike Yelahanka Project Division Bengaluru.							
Name of Project & Address	Improvements to Someshwara Hill and Surrounding areas at attur, Ward No-03 in Yelahanka Satellite Town Sub Division.							
Name of Consultant	M/s DSR Infratech, 1594, 3rd main, Judicial Layout, Yelahanka, Bengaluru.							
Name of Agency	Mr.Gopi Reddy						Bengaluru.	
Clients Letter Dated	25.06.2022							
Date of Sample Received	25.06.2022							
Source of Sample	Supplied by the Client							
Dimensions of Specimens in mm	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
Grade of Concrete	M20							
Compressive Strength test as per guidelines of IS-516-1959 has been conducted on the concrete cube specimens								
SI No	Cubes Pertaining to the concrete Cast at*(Details of structural Member Identification	Date of Casting*	Date of Testing	Age of Concrete on the date of test** (Days)	Contact Area (mm ²)	Weight of Specimen (gm)	Load In KN	Compressive Strength in Nmm ²
1	Plinth Beam Concrete (Compound Work)	28.05.2022	25.06.2022	28 Days	22500.00	8065	632.2	28.10
2		28.05.2022	25.06.2022		22500.00	8042	625.4	27.80
3		28.05.2022	25.06.2022		22500.00	8057	630.8	28.04

1N/Sq.mm=10kg/Sq.cm(Approx)

* As furnished by the client

Note; A Minimum of three cube specimens shall be supplied for testing as per IS:516-1959

For Karnataka Material Test House Pvt Ltd.,

Prepared & Checked by
Nagaraj K S

Approved by
Narayanswamy.B



End of Report. Asst. Executive Engineer
Project Division

Note:

- 1)This reports is not to be reproduced except in full without our prior permission in writing.
- 2)The results listed refer only to the tested samples nd applicable parameters.
- 3)Any correction in the report will be invalid.



Off & Lab :No. 8 (10/3), 4th cross, Basaveshwara layout, Nagashettihalli, RMV 2nd Stage, BENGALURU 560094
080- 2341 8668, 23511213 Mobile: 94485 15258 E-mail: kmthblr@gmail.com www.karnatakamaterialtesthouse.com
M/s Karnataka Consultancy Services is Sister Concern of KMTHPL



Karnataka Material Test House Pvt. Ltd.,

Soil Investigation, Concrete and NDT Testing, Topo Survey, & Project management Consultancy

CIN No: U74210KA2004PTC035137 G S T No: 29AACCK4994Q1ZI PAN No: AACCK4994Q

IR

Report No	KMT/ Cubes/3620/2022-23						Date	30.06.2022
TEST RESULTS ON CONCRETE CUBES								
Name of Client & Address	Bruhat Bengaluru Mahanagara Palike Yelahanka Project Division Bengaluru.							
Name of Project & Address	Improvements to Someshwara Hill and Surrounding areas at attur, Ward No-03 in Yelahanka Satellite Town Sub Division.							
Name of Consultant	M/s DSR Infratech, 1594, 3rd main, Judicial Layout, Yelahanka, Bengaluru.							
Name of Agency	Mr.Gopi Reddy Bengaluru.							
Clients Letter Dated	29.06.2022							
Date of Sample Received	29.06.2022							
Source of Sample	Supplied by the Client							
Dimensions of Specimens in mm	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
Grade of Concrete	M20							
Compressive Strength test as per guidelines of IS-516-1959 has been conducted on the concrete cube specimens supplied by								
Sl No	Cubes Pertaining to the concrete Cast at*(Details of structural Member Identification)	Date of Casting*	Date of Testing	Age of Concrete on the date of test** (Days)	Contact Area (mm ²)	Weight of Specimen (gm)	Load In KN	Compressive Strength in Nmm ²
1	Column Concrete (Compound Work)	22.06.2022	29.06.2022	7 Days	22500.00	8326	408.4	18.15
2		22.06.2022	29.06.2022		22500.00	8241	405.4	18.02
3		22.06.2022	29.06.2022		22500.00	8246	409.0	18.18

1N/Sq.mm=10kg/Sq.cm(Approx)
Note; A Minimum of three cube specimens shall be supplied for testing as per IS:516-1959

For Karnataka Material Test House Pvt Ltd.,

Prepared & Checked by
Nagaraj K S

Approved by
Narayanswamy.B



.....End of Report.....
Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

Note: 1)This reports is not to be reproduced except in full without our prior permission in writing.
2)The results listed refer only to the tested samples and applicable parameters.
3)Any correction in the report will be invalid.



Off & Lab :No. 8 (10/3), 4th cross, Basaveshwara layout, Nagashettihalli, RMV 2nd Stage, BENGALURU 560094
80- 2341 8668, 23511213 Mobile: 94485 15258 E-mail: kmthblr@gmail.com www.karnatakamaterialtesthouse.com
M/S Karnataka Consultancy Services is Sister Concern of KMTPL



Karnataka Material Test House Pvt. Ltd.,

Soil Investigation, Concrete and NDT Testing, Topo Survey, & Project management Consultancy

CIN No: U74210KA2004PTC035137 G S T No: 29AACCK4994Q1ZI PAN No: AACCK4994Q

Report No	KMTH/Cubes/3621/2022-23						Date	21.07.2022
TEST RESULTS ON CONCRETE CUBES								
Name of Client & Address	Bruhat Bengaluru Mahanagara Palike Yelahanka Project Division Bengaluru.							
Name of Project & Address	Improvements to Someshwara Hill and Surrounding areas at attur, Ward No-03 in Yelahanka Satellite Town Sub Division.							
Name of Consultant	M/s DSR Infratech, 1594, 3rd main, Judicial Layout, Yelahanka, Bengaluru.							
Name of Agency	Mr.Gopi Reddy							
Clients Letter Dated	20.07.2022							
Date of Sample Received	20.07.2022							
Source of Sample	Supplied by the Client							
Dimensions of Specimens in mm	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
Grade of Concrete	M20							
Compressive Strength test as per guidelines of IS-516-1959 has been conducted on the concrete cube specimens								
SI No	Cubes Pertaining to the concrete Cast at* (Details of structural Member Identification)	Date of Casting*	Date of Testing	Age of Concrete on the date of test** (Days)	Contact Area (mm ²)	Weight of Specimen (gm)	Load In KN	Compressive Strength in Nmm ²
1	Column Concrete (Compound Work)	22.06.2022	20.07.2022	28 Days	22500.00	8142	625.8	27.81
2		22.06.2022	20.07.2022		22500.00	8166	628.4	27.93
3		22.06.2022	20.07.2022		22500.00	8089	626.4	27.84

1N/Sq.mm=10kg/Sq.cm(Approx)
Note; A Minimum of three cube specimens shall be supplied fo testing as per IS:516-1959

For Karnataka Material Test House Pvt Ltd.,

Prepared & Checked by
Nagaraj K S

Approved by
Narayanswamy.B

.....End of Report.....

Note:

- 1)This reports is not to be reproduced except in full without our prior permission in writing.
- 2)The results listed refer only to the tested samples nd applicable parameters.
- 3)Any correction in the report will be invalid.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92



Off & Lab :No. 8 (10/3), 4th cross, Basaveshwara layout, Nagashettihalli, RMV 2nd Stage, BENGALURU 560094
80- 2341 8668, 23511213 Mobile: 94485 15258 E-mail: kmthblr@gmail.com www.karnatakamaterialtesthouse.com
M/s Karnataka Consultancy Services is Sister Concern of KMTHPL



Karnataka Material Test House Pvt. Ltd.,

Soil Investigation, Concrete and NDT Testing, Topo Survey, & Project management Consultancy

CIN No: U74210KA2004PTC035137 G S T No: 29AAGCK4994G1Z1 PAN No: AAGGR4994G

Report No	KMTH/Cubes/3622/2022-23					Date	18.04.2022	
TEST RESULTS ON CONCRETE CUBES								
Name of Client & Address		Bruhat Bengaluru Mahanagara Palike Yelahanka Project Division Bengaluru.						
Name of Project & Address		Improvements to Someshwara Hill and Surrounding areas at attur, Ward No-03 in Yelahanka Satellite Town Sub Division.						
Name of Consultant		M/s DSR Infratech, 1594, 3rd main, Judicial Layout, Yelahanka, Bengaluru.						
Name of Agency		Mr.Gopi Reddy Bengaluru.						
Clients Letter Dated		16.04.2022						
Date of Sample Received		16.04.2022						
Source of Sample		Supplied by the Client						
Dimensions of Specimens in mm		150.0	x	150.0	x	150.0		
		150.0	x	150.0	x	150.0		
		150.0	x	150.0	x	150.0		
Grade of Concrete		M20						
Compressive Strength test as per guidelines of IS-516-1959 has been conducted on the concrete cube specimens supplied by								
Sl No	Cubes Pertaining to the concrete Cast at*(Details of structural Member Identification	Date of Casting*	Date of Testing	Age of Concrete on the date of test** (Days)	Contact Area (mm ²)	Weight of Specimen (gm)	Load in KN	Compressive Strength in Nmm ²
1	Footing	09.04.2022	16.04.2022	7 Days	22500.00	8240	410.8	18.26
2	Concrete	09.04.2022	16.04.2022		22500.00	8256	411.5	18.29
3	(Toilet Building)	09.04.2022	16.04.2022		22500.00	8266	409.4	18.20

1N/Sq.mm=10kg/Sq.cm(Approx)

* As furnished by the client

Note: A Minimum of three cube specimens shall be supplied for testing as per IS:516-1959

For Karnataka Material Test House Pvt Ltd.,

Prepared & Checked by
Nagaraj K S

.....End of Report.....

Approved by
Narayanswamy B.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore

- Note:
- 1) This report is not to be reproduced except in full without our prior permission in writing.
 - 2) The results listed refer only to the tested samples and applicable parameters.
 - 3) Any correction in the report will be invalid.



Off & Lab : No. 8 (10/3), 4th cross, Basaveshwara layout, Nagashettihalli, RMV 2nd Stage, BENGALURU 560094
:080- 2341 8668, 23511213 Mobile: 94485 15258 E-mail: kmthblr@gmail.com www.karnatakamaterialtesthouse.com
M/s Karnataka Consultancy Services is Sister Concern of KMTHPL



Karnataka Material Test House Pvt. Ltd.,

CIN No: U74210KA2004PTC035137 G S T No: 29AACCK4994Q1Z1 PAN No: AACCK4994Q

Report No	KMTH/Cubes/3623/2022-23					Date	09.05.2022	
TEST RESULTS ON CONCRETE CUBES								
Name of Client & Address	Bruhat Bengaluru Mahanagara Palike Yelahanka Project Division Bengaluru.							
Name of Project & Address	Improvements to Someshwara Hill and Surrounding areas at attur, Ward No 03 in Yelahanka Satellite Town Sub Division.							
Name of Consultant	M/s DSR Infratech, 1594, 3rd main, Judicial Layout, Yelahanka, Bengaluru.							
Name of Agency	Mr.Gopi Reddy Bengaluru.							
Clients Letter Dated	07.05.2022							
Date of Sample Received	07.05.2022							
Source of Sample	Supplied by the Client							
Dimensions of Specimens in mm	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
Grade of Concrete	M20							
Compressive Strength test as per guidelines of IS-516-1959 has been conducted on the concrete cube specimens								
Sl No	Cubes Pertaining to the concrete Cast at*(Details of structural Member Identification	Date of Casting*	Date of Testing	Age of Concrete on the date of test** (Days)	Contact Area (mm ²)	Weight of Specimen (gm)	Load In KN	Compressive Strength in Nmm ²
1	Footings Concrete (Toilet Building)	09.04.2022	07.05.2022	28 Days	22500.00	8120	623.4	27.71
2		09.04.2022	07.05.2022		22500.00	8136	624.2	27.74
3		09.04.2022	07.05.2022		22500.00	8147	628.4	27.93

1N/Sq.mm=10kg/Sq.cm(Approx)

* As furnished by the client

Note; A Minimum of three cube specimens shall be supplied for testing as per IS:516-1959

For Karnataka Material Test House Pvt Ltd.,

Prepared & Checked by
Nagaraj K S

Approved by
Narayanswamy.B

End of Report.....

Note:

- 1)This reports is not to be reproduced except in full without our prior permission in writing.
- 2)The results listed refer only to the tested samples and applicable parameters.
- 3)Any correction in the report will be invalid.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore



Off & Lab :No. 8 (10/3), 4th cross, Basaveshwara layout, Nagashettihalli, RMV 2nd Stage, BENGALURU 560094
:080- 2341 8668, 23511213 Mobile: 94485 15258 E-mail: kmthblr@gmail.com www.karnatakamaterialtesthouse.com
M/s Karnataka Consultancy Services is Sister Concern of KMTHPL



Karnataka Material Test House Pvt. Ltd.,

Soil Investigation, Concrete and NDT Testing, Topo Survey, & Project management Consultancy

CIN No: U74210KA2004PTC035137 G S T No: 29AACCK4994Q1ZI PAN No: AACCK4994Q

Report No	KMTH/Cubes/3624/2022-23						Date	06.06.2022
TEST RESULTS ON CONCRETE CUBES								
Name of Client & Address	Bruhat Bengaluru Mahanagara Palike Yelahanka Project Division Bengaluru.							
Name of Project & Address	Improvements to Someshwara Hill and Surrounding areas at attur, Ward No-03 in Yelahanka Satellite Town Sub Division.							
Name of Consultant	M/s DSR Infratech, 1594, 3rd main, Judicial Layout, Yelahanka, Bengaluru.							
Name of Agency	Mr.Gopi Reddy Bengaluru.							
Clients Letter Dated	04.06.2022							
Date of Sample Received	04.06.2022							
Source of Sample	Supplied by the Client							
Dimensions of Specimens in mm	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
	150.0	x	150.0	x	150.0			
Grade of Concrete	M20							
Compressive Strength test as per guidelines of IS-516-1959 has been conducted on the concrete cube specimens supplied by								
Sl No	Cubes Pertaining to the concrete Cast at*(Details of structural Member Identification)	Date of Casting*	Date of Testing	Age of Concrete on the date of test** (Days)	Contact Area (mm ²)	Weight of Specimen (gm)	Load In KN	Compressive Strength in Nmm ²
1	Roof Slab Concrete (Toilet Building)	28.05.2022	04.06.2022	7 Days	22500.00	8286	412.8	18.35
2		28.05.2022	04.06.2022		22500.00	8269	416.2	18.50
3		28.05.2022	04.06.2022		22500.00	8276	419.4	18.64

1N/Sq.mm=10kg/Sq.cm(Approx)
Note; A Minimum of three cube specimens shall be supplied for testing as per IS:516-1959

For Karnataka Material Test House Pvt Ltd.,

Prepared & Checked by
Nagaraj K S

.....End of Report.....

Approved by
Narayanswamy.B



Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

Note: 1)This reports is not to be reproduced except in full without our prior permission in writing.
2)The results listed refer only to the tested samples and applicable parameters.
3)Any correction in the report will be invalid.



Off & Lab :No. 8 (10/3), 4th cross, Basaveshwara layout, Nagashettihalli, RMV 2nd Stage, BENGALURU 560094
1.:080- 2341 8668, 23511213 Mobile: 94485 15258 E-mail: kmthblr@gmail.com www.karnatakamaterialtesthouse.com
M/s Karnataka Consultancy Services is Sister Concern of KMTHPL

Karnataka Material Test House Pvt. Ltd.,

Soil Investigation, Concrete and NDT Testing, Topo Survey, & Project management Consultancy

CIN No: U74210KA2004PTC035137 GST No: 29AAGCK4994G121 PAN No: AACCK4994G

KMTH/Cubes/3626/2022-23

TEST RESULTS ON CONCRETE CUBES

Client & Address	Bruhat Bengaluru Mahanagara Palike Yelahanka Project Division Bengaluru.	Date	27.06.2022
Project & Address	Improvements to Someshwara Hill and Surrounding areas at attur, Ward No-03 in Yelahanka Satellite Town Sub Division.		
Consultant	M/s DSR Infratech, 1594, 3rd main, Judicial Layout, Yelahanka, Bengaluru.		
Agency	Mr.Gopi Reddy		
Letter Dated	25.06.2022		
Sample Received	25.06.2022		Bengaluru.
Source of Sample	Supplied by the Client		
Dimensions of Specimens in mm	150.0 x 150.0 x 150.0	x	150.0
	150.0 x 150.0 x 150.0	x	150.0
	150.0 x 150.0 x 150.0	x	150.0
	M20	x	150.0

Sl No	Cubes Pertaining to the concrete Cast at*(Details of structural Member Identification)	Date of Casting*	Date of Testing	Age of Concrete on the date of test** (Days)	Contact Area (mm²)	Weight of Specimen (gm)	Load in KN	Compressive Strength in Nmm²
1	Roof Slab Concrete	28.05.2022	25.06.2022	28	22500.00	8200	625.4	27.80
2	(Toilet Building)	28.05.2022	25.06.2022	28	22500.00	8212	615.4	27.35
3		28.05.2022	25.06.2022	28	22500.00	8216	619.8	27.55

Compressive Strength test as per guidelines of IS-516-1959 has been conducted on the concrete cube specimens

* As furnished by the client

1N/Sq.mms.10kg/Sq.cm(Approx)

Note: A Minimum of three cube specimens shall be supplied for testing as per IS:516-1959

For Karnataka Material Test House Pvt Ltd.,

Prepared & Checked by
Nagaraj K S

.....End of Report.....

Approved by
Narayanswamy.B

Note:

- 1)This reports is not to be reproduced except in full without our prior permission in writing.
- 2)The results listed refer only to the tested samples nd applicable parameters.
- 3)Any correction in the report will be invalid.

Off & Lab :No. 8 (10/3), 4th cross, Basaveshwara layout, Nagashettihalli, RMV 2nd Stage, BENGALURU 560094

Ph.:080- 2341 8668, 23511213 Mobile: 94485 15258 E-mail: kmthblr@gmail.com www.karnatakamaterialtesthouse.com

M/s Karnataka Consultancy Services is Sister Concern of KMTHPL